



IGUAÇU
celulose, papel s.a.



TECHNICAL DATA SHEET

EXTENSIBLE SACK KRAFT 85 gsm

Properties	UNITS	Typical
Basis Weight	g /m ²	85,0
Moisture	%	6,9
Muellen	kPa	346
Tear MD	mN	1030
Tear CD	mN	1288
Tensile Strenght MD	kN/m	4,7
Tensile Strenght CD	kN/m	3,8
Stretch MD	%	11,8
Stretch CD	%	8,4
Cobb	g/m ²	40,0
Air Resistance (Gurley)	s /100ml	11
Tea MD	J/m ²	321,35
Tea CD	J/m ²	213,11
Tea Balanced	J/m ²	246,76

The production of Extensible Sack Kraft Paper is certified according to the quality management system ISO 9001 by IQNET.
The Standard kraft paper is produced with 100% Unbleached Softwood Pulp.

Packing set

cardboard core, plug, plastic layer, liner and lateral disc